

ชื่อเรื่องการค้นคว้าแบบวิสรະเชิงวิทยานิพนธ์

การศึกษาโครงสร้างพล็อกของแนวเรียนพิเศษนักท่องเที่ยว

ອຸ່ນທະນາຄານ

ก้าวผู้เรียน

นายอนันต์ วิริยะกุล

คณิตศาสตร์ฐานสุนทรีย์คณิตศาสตร์เชิงวิทยาพินธ์

รองศาสตราจารย์ ดร. กวี ตันฉัตรี

ผู้ช่วยศาสตราจารย์ นรินทร์ สิริรัตน์วัฒนาล

ผู้ช่วยศาสตราจารย์ รักนิ ศิริพันธุ์

ประมวลผลการ

กิจกรรมการ

ก้าวต่อไป

Impressions

การวิเคราะห์โครงสร้างผลึกของแบบเรียบติตาเนต เตรียมจากแบบเรียบติตาเนต และติตาเนียมออกไซด์ผสมกันในอัตราส่วนต่อโมลของสารทึ้งสองเท่ากัน, เติมสารเจือニโวเบียมออกไซด์ และผสมสตอรอนเตรียมคาร์บอเนต ในอัตราส่วนต่าง ๆ กันแล้วนำไปเผาแคลโลไนซ์ที่ 1000 องศาเซลเซียส 1 ชั่วโมง อัดเป็นรูปทรงกรวยออกใช้ความดัน 700-2400 กิโลกรัม/ตารางเซนติเมตร นำไปบรินเนอร์ที่ 1340-1440 องศาเซลเซียส 1-3 ชั่วโมง การวิเคราะห์โดยใช้ติฟแฟร์คให้มีเทอร์ พบร้าเป็นแบบเรียบติตาเนตที่มีโครงสร้างในระบบเตตราゴโนล จากการศึกษาโครงสร้างจุลภาคโดยใช้กล้องจุลทรรศน์ไฟ拉ไวร์ อาศัยการวิเคราะห์ความแปรปรวน พบร้าที่ระดับนัยสำคัญ 0.10 อุณหภูมิ, ความดัน, ปริมาณของสารเจือที่เติมและอัตราส่วนการผสมมีผลต่อ grain size และ grain area โดยอุณหภูมิเพิ่ม grain size จะเพิ่ม, ความดันเพิ่ม grain size จะลด ปริมาณการเติมสารเจือและอัตราส่วนการผสมเพิ่ม grain size และ grain area จะลด

Research Title A Study of Crystal Structure of Barium Titanate at Various Temperatures

Author Mr. Tanoo Kruthakool

M.S. Teaching Physics

Examining Committee :

Assoc. Prof. Dr. Tawee Tunkasiri	Chairman
----------------------------------	----------

Assist. Prof. Narin Siriratwatanakul	Member
--------------------------------------	--------

Assist. Prof. Rajanee Tiyapun	Member
-------------------------------	--------

Abstract

The analysis of crystal structure of BaTiO_3 which prepared from BaCO_3 and TiO_2 of equimolar concentration, doped with Nb_2O_5 and mixed with SrCO_3 in various ratios. The mixture was calcined at 1000°C for 1 hour. The mixture solid is pressed and shaped into a cylindrical form at the pressure of $700-2400 \text{ kg/cm}^2$ and then sintered at $1340-1440^\circ\text{C}$ for 1-3 hours. By diffractometer analysis it was found that the crystal structure of BaTiO_3 was tetragonal system. By microstructure studies using the polarizing microscope and by analysis of variance it was found that at significant of 0.10, grain size and grain area are dependent of annealing temperature, pressure, dopant content and mixture ratio. Grain size was found to increase with the rising annealing temperature but with increasing pressure, dopant contents and mixture ratio grain size and grain area were found to decrease.