


ขอเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์

การเตรียมสารตัวนำยังไง



ชื่อผู้เขียน

รท. บุญมีนคร สร้างเมือง

วิทยาศาสตรมหาบัณฑิต

สาขาวิชาสอนพิสิกส์

คณะกรรมการตรวจสอบการค้นคว้าแบบอิสระ เชิงวิทยานิพนธ์

รศ. ดร. นิกร มั่นกรทอง

ประธานกรรมการ

รศ. สุภาพ พ. เชียงใหม่

กรรมการ

ผศ. ดร. ศรีเพ็ญ ท้าวคาน

กรรมการ

บทคัดย่อ

ในงานนี้จัดขึ้นได้เตรียมสารตัวนำยังไงด้วยวิธีอุณหภูมิสูง $\text{YBa}_2\text{Cu}_3\text{O}_{9-\delta}$ โดยวิธีปฏิกิริยาของแข็ง (Solid Reaction) จากสารเริ่มตน Y_2O_3 , BaCO_3 และ CuO ด้วยสัดส่วนจำนวนอะตอมของ $\text{Y}:\text{Ba}:\text{Cu}$ เป็น $1:2:3$ ครั้งแรกทำการเผาองของลวนผสมที่อุณหภูมิในช่วง $900-950^\circ\text{C}$ ในบรรยายกาศออกซิเจน แล้วนำมาอัดเม็ดและเผาในบรรยายกาศออกซิเจนเช่นเดียวกัน พบว่าสารที่เตรียมได้แสดงปรากฏการณ์ไมซ์เนอร์ (Meissner effect) ที่อุณหภูมิเน้นอุณหภูมิของในโคลเจนเหลว จากการวัดสภาพต้านทานไฟฟ้าพบว่าอุณหภูมิวิกฤต (Critical Temperature) ของสารที่เตรียมได้อยู่ในช่วง $93-94\text{ K}$ ทำการวิเคราะห์โครงสร้างโดยใช้การเลือยabeenของรังสีเอ็กซ์ (X-ray-Diffraction) พบว่าโครงสร้างเป็นแบบออร์โทรมนิกเพอร์อฟส์ไกค์ (Orthorhombic Perovskite) มีพารามิเตอร์ลักษณะ (Lattice Parameter) $a = 3.87\text{ \AA}$, $b = 3.68\text{ \AA}$ และ $c = 11.45\text{ \AA}$

Research Title Preparation of the Superconductor $\text{YBa}_2\text{Cu}_3\text{O}_{9-\delta}$

Author LT. Pathomnakorn Srangarim

M.S. Teaching Physics

Examining Committee

Assoc. Prof. Dr. Nikorn Mangkorntong Chairman

Assoc. Prof Suparb Na Chiangmai Member

Assist. Prof. Dr. Sripen Towta Member

Abstract

In this work high T_c superconductor $\text{YBa}_2\text{Cu}_3\text{O}_{9-\delta}$ was prepared by solid reaction from the starting compound Y_2O_3 , BaCO_3 and CuO . Atomic composition ratio of Y:Ba:Cu was 1:2:3. The well-mixed powder was first preheated at temperature in the range of $900\text{-}950^\circ\text{C}$ in oxygen atmosphere. Then samples in the form of pellets was sintered, also in oxygen atmosphere. Meissner effect was observed at temperature near the boiling point of liquid nitrogen. Critical temperature was observed by means of resistivity measurement and was found to be in the range of 93-94 K. Crystal structure of the samples was identified by means of X-ray diffraction to be orthorhombic perovskite, with lattice parameters $a = 3.87 \text{ \AA}$, $b = 3.68 \text{ \AA}$, and $c = 11.45 \text{ \AA}$.