

ชื่อเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ การเติร์นเซรามิกส์ทันไฟท์มีสภาพนำความร้อนสูง

ชื่อผู้เขียน นายสุวิช ชนวนสุกี้

วิทยาศาสตรมหาบัณฑิต สาขางานสอนฟิลิกส์

คณะกรรมการตรวจสอบการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์

รศ. จีระพงษ์ ตันตราภรณ์

ประธานกรรมการ

รศ. ดร. กวี ตันตระกิริ

กรรมการ

ผศ. นรินทร์ ลิริกุลรัตน์

กรรมการ

### บทคัดย่อ

งานวิจัยนี้ ประกอบด้วย สารตัวอย่าง 2 ชุด ชุดแรกเป็นการผสมระหว่างแกรไนท์กับดินเกลิน และชิลิกอนคาร์บอเนต, แกรไฟท์กับดินเกลิน ส่วนอีกชุดหนึ่งเป็นการผสมระหว่างชิลิกอนคาร์บอเนตกับดินเกลิน แมกนีเซียมออกไซด์กับดินเกลิน และแมกนีเซียมออกไซด์, ชิลิกอนคาร์บอเนตกับดินเกลิน ชุดแรกเผาที่อุณหภูมิ 1,000, 1,150 และ 1,250 องศาเซลเซียส ส่วนชุดที่สองที่ 1,100, 1,250 และ 1,350 องศาเซลเซียส ระยะเวลาการเผา 3 ชั่วโมง ผลการค่าปรากฏว่า ค่าสภาพนำความร้อนที่สูงกว่ากับสมบัติของสารที่นำมาผสมกัน เมื่อเผาที่อุณหภูมิสูงที่ค่าสภาพนำความร้อนและค่าความร้อนและค่าสภาพนำไฟฟ้ามีแนวโน้มลดลง ผลการทดลองพบว่า เซรามิกส์ทันไฟท์มีส่วนผสมระหว่างชิลิกอนคาร์บอเนตดินเกลิน เท่ากับ 75:25 เผาที่อุณหภูมิ 1,350 องศาเซลเซียส เวลา 3 ชั่วโมง จะมีค่าสภาพนำความร้อนสูงสุดเท่ากับ  $3.375 \text{ W/m}^2\text{C}$  มีค่าความนรุนเท่ากับ 20.67% และมีค่าความแกร่งเท่ากับ  $28.310 \text{ MN/m}^2$

Research Title      Preparation of High Thermal Conductivity Refractory Ceramics

Author                Mr. Suvich Samapisut

M.S.                 Teaching Physics

Examining Committee:

Assoc. Jerapong	Tantrakoon	Chairman
Assoc. Dr. Tawee	Tunkasiri	Member
Assist. Narin	Sirikulrat	Member

### Abstract

In this research, 2 set of samples were employed. The first set were the mixtures of graphite and kaolin, and silicon carbide, graphite and kaolin. The second set were the mixtures of silicon carbide and kaolin, manesium oxide and kaolin, and lastly magnesium oxide, silicon carbide and kaolin. The first set was fired at  $1,000^{\circ}\text{C}$ ,  $1,150^{\circ}\text{C}$  and  $1,250^{\circ}\text{C}$ . The second set was fired at  $1,100^{\circ}\text{C}$ ,  $1,250^{\circ}\text{C}$  and  $1,350^{\circ}\text{C}$ . The annealing time was 3 hours for every set of the samples. Then the study of thermal conductivity, porosity, strength and electrical conductivity were carried out. It was found that thermal conductivities and strength of samples increased with increasing firing temperatures, while porosities and electrical conductivities of samples decreased with increasing firing temperatures. The sample prepared using the mixture of silicon carbide and kaolin in proportions of 75:25 sinter at  $1,350^{\circ}\text{C}$  for 3 hours, shows high value of thermal conductivity of  $3.375 \text{ W/m}^{\circ}\text{C}$  gave porosity of 20.67% and strength of  $28.310 \text{ MN/m}^2$ .