

## APPENDIX

Table A. Shear bond strength values for different adhesive systems

No	Shear bond strength (in MPa)					
	Group 1	Group 2	Group 3	Group 4	Group 5	Group 6
1	9.665	8.039	14.439	1.379	11.240	16.097
2	11.518	8.097	15.007	1.442	7.307	14.550
3	11.815	11.856	11.145	0.775	5.880	12.873
4	10.619	15.573	14.568	8.760	13.240	17.774
5	8.820	9.824	14.501	10.040	13.150	13.295
6	11.417	12.757	16.421	1.370	11.130	13.765
7	11.484	15.893	15.391	5.870	2.248	12.043
8	12.240	12.832	14.423	4.930	6.119	13.487
9	9.325	9.448	12.652	9.922	11.652	9.296
10	9.540	7.304	16.990	7.603	6.720	5.431
11	6.308	11.134	13.645	11.372	2.117	13.630
12	11.072	11.103	11.970	7.934	1.233	7.266
13	9.540	10.755	12.898	11.004	1.389	9.007
14	12.406	12.551	12.166	10.467	3.036	14.534
15	12.310	13.295	10.816	4.774	9.388	12.724
16	6.782	13.987	13.841	9.720	10.937	11.561
17	11.369	12.130	14.355	5.226	3.806	14.057
18	8.756	12.877	14.907	3.376	14.023	11.418
19	13.231	10.400	14.840	4.832	14.803	10.531
20	6.896	12.065	12.290	9.537	0.902	12.593

Table B. Adhesive Remnant Index for different adhesive systems

No	ARI score					
	Group 1	Group 2	Group 3	Group 4	Group 5	Group 6
1	1	1	3	0	1	3
2	1	1	3	0	1	3
3	2	1	2	0	1	2
4	2	2	3	1	2	3
5	1	1	3	1	2	3
6	2	1	3	0	1	3
7	2	2	3	1	1	2
8	2	1	3	1	1	3
9	1	1	2	1	2	2
10	1	1	3	1	1	1
11	1	2	3	2	1	3
12	2	2	2	1	0	1
13	1	1	3	2	0	1
14	2	2	2	1	1	3
15	2	2	2	0	1	2
16	1	2	3	1	1	1
17	2	2	3	1	1	3
18	1	2	3	1	2	2
19	3	1	3	1	2	2
20	1	2	3	1	0	3

## CURRICULUM VITAE

**Name** Mr. Kittinunt Chotikaew

**Date of Birth** 4 April 1977

**Institution attended:**

1994 - 2000 Prince of Songkla University

Doctor of Dental Surgery (D.D.S Hons.)

**Position held and office:**

2000 – 2007 Dental Health Section, Nongjik Hospital, Nongjik District,

Pattani Province, Thailand

ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่

Copyright© by Chiang Mai University

All rights reserved