ชื่อเรื่องวิทยานิพน**ห์** 

โมคูลัสการคืนตัวของวัสคุมวลรวมในภาคเหนือของ ประเทศไทยที่ปรับปรุงคุณสมบัติด้วยปุ่นซีเมนต์

ชื่อผู้เขียน

**€** 

C

นางสาวจีริกุล บุญคำ

วิศวกรรมศาสตรมหาบัณฑิต

สาขาวิชาวิศวกรรมโยหา

<sup>คณะกรรมการสอบวิทยานิพนธ์</sup>

ผศ. คร. อนิรุทธ์ ธงใชย ประชานกรรมการ รศ. สูเทพ นิ่มนวล

กรรมการ

ผส. คร. บุญเทพ นาเนกรังสรรค์ กรรมการ

ศ. ดร. ดิเรก ถาวัณย์ศิริ

กรรมการ

## บทคัดย่อ

วิทยานิพนธ์นี้มีวัตถุประสงค์ในการศึกษาความสัมพันธ์ระหว่างค่าโมคูลัสการคืนตัวกับ คุณสมบัติจากการทคสอบกำลังรับแรงอัคทางเคียวของวัสคุมวลรวมในภาคเหนือของประเทศไทยที่ ปรับปรุงคุณสมบัติด้วยปูนซีเมนต์ โดยในการศึกษาได้เก็บตัวอย่างดินจากแหล่งต่างๆ 3 ชนิด คือ ดินลูกรัง ดินกรวด และ ดินจากหินแกรนิตผุ ทำการผสมด้วยปูนซีเมนต์ในอัตราส่วนผสมร้อยละ 2 10 และบคอัคตัวอย่างดินที่ระดับความแน่นเท่ากับความแน่นแห้งสูงสุด และบ่มที่สภาพ ความชื้นที่อุณหภูมิห้องจนอายุครบ 7 วัน ก่อนนำไปทำการทคสอบหาค่ากำลังรับแรงอัดทางเคียว ควบคู่กับการทคสอบหาค่าโมคูลัสการคืนตัว โคยวิธีการให้แรงคึงทางอ้อมและวิธีให้แรงอัคสาม แกน

ในการทคสอบกำลังรับแรงอัดทางเคียวพบว่า ค่ากำลังรับแรงอัคทางเคียวของตัวอย่างคินทั้ง สามชนิคเพิ่มขึ้นเป็นสัคส่วนกับปริมาณปูนซีเมนต์ที่ใช้ผสม แต่อัตราการเพิ่มนี้จะแตกต่างกันไป โดยพบว่าดินกรวดและดินจากหินแกรนิตผูที่มีขนาคคละค่อนข้างดีและมีมวล ตามชนิดของคืน ละเอียดปนน้อย มีอัตราการเพิ่มของกำลังรับแรงอัดทางเดียวสูงกว่าดินลูกรังที่มีขนาดคละด้อยกว่า และมีมวลละเอียคที่มีความเหนียวปนมากกว่า ในส่วนของความสัมพันธ์ระหว่างแรงเค้นและ ความเครียดนั้นพบว่า ค่าโมคูลัสยีคหยุ่น  $E_{so}$  ก็เพิ่มขึ้นเป็นสัคส่วนกับปริมาณปู่นซีเมนต์ที่ใช้ผสม เช่นเดียวกัน โคยพบว่าคินกรวคซึ่งมีขนาดคละคืและมีเม็ดหยาบที่แกร่งมีอัตราการเพิ่มมากที่สุด ส่วนดินจากหินแกรนิตผุซึ่งมีเม็ดหยาบเปราะแตกหักได้ง่ายกว่ามีค่า โมคูลัสยีคหยุ่น  $E_{so}$  ต่ำกว่าของ คินกรวคแม้ว่าคินทั้งสองชนิดจะมีลักษณะการกระจายขนาดคละและความเหนียวใกล้เคียงกัน สำหรับคินลูกรังที่มีขนาดคละด้อยกว่าและมีความเหนียวมากกว่ามีอัตราเพิ่มน้อยที่สุด นอกจากนี้ยัง พบว่าค่า โมคูลัสความยืดหยุ่น  $E_{so}$  มีแนว โน้มที่จะสัมพันธ์กับค่ากำลังรับแรงอัดทางเดียวในรูป สมการเส้นตรงสำหรับคินกูกรั้งและคินจาก หินแกรนิตผู แต่สำหรับคินกรวคสมการเส้นตรงมีความชันมากกว่า

จากการทดสอบหาค่า โมดูลัสการคืนตัวพบว่าค่า โมดูลัสการคืนตัวจากการทดสอบ โดยวิธีให้ แรงคึ่งทางอ้อมมีแนว โน้มการเปลี่ยนแปลงตามคุณสมบัติของคินและปริมาณปูนซีเมนต์ที่ผสม เหมือนกับค่า โมดูลัสยีคหยุ่น E<sub>50</sub> แต่ค่าที่ ได้จะสูงกว่าและยังพบว่า ค่า โมดูลัสการคืนตัวที่ทคสอบ ได้ ในการศึกษาครั้งนี้มีค่าสูงกว่าค่าที่รายงาน โดยผู้วิจัยอื่น ทั้งนี้กาดว่าเป็นเพราะระดับแรงกระทำที่ใช้ ในการทดสอบค่อนข้างต่ำลือประมาณร้อยละ 3.0 ของค่ากำลังรับแรงอัดทางเคียว ส่วนค่า โมคูลัส การคืนตัวจากการทดสอบแบบให้แรงอัดสามแกน ไม่แสดงแนว โน้มการเปลี่ยนแปลงตามชนิดของ คินและปริมาณปูนซีเมนต์ที่ใช้ผสมอย่างชัดเจน

จากการวิเคราะห์หาความสัมพันธ์ระหว่าง โมดูถัสการคืนตัวจากวิธีทคสอบแบบให้แรงคึง ทางอ้อมกับกำลังรับแรงอัดทางเคียวพบว่าความสัมพันธ์จะแตกต่างกันไปตามชนิดของดิน อย่างไร ก็ตามเมื่อนำเอาค่า โมดูถัสการคืนตัวมาเทียบหาความสัมพันธ์กับค่า โมดูถัสยึดหยุ่นจากการทคสอบ กำลังรับแรงอัดทางเคียวพบว่า สามารถใช้สมการความสัมพันธ์  $M_R=21~(E_{50})$  ได้กับดินทั้งสาม ชนิด ซึ่งสมการนี้มีค่าสัมประสิทธิ์ตัวกำหนดเท่ากับ 0.893 และมีความเชื่อถือได้ที่ระดับความ เชื่อมั่นร้อยละ 95

**C**,

()

Thesis Title

Resilient Modulus of Cement Stabilized Soil

Aggregates of Northern Thailand

Author

Ms. Jeerikun Boonkhum

M. Eng

Civil Engineering

**Examining Committee** 

Asst. Prof. Dr. Aniruth Thongchai

Chairman

Assoc. Prof. Suthep Nimnual

Member

Asst. Prof. Dr. Boonthep Nanegrungsun

Member

Prof. Dr. Direk Lavansiri

Member

## **ABSTRACT**

The purpose of the study in this thesis is to investigate relationships between values of resilient modulus and engineering properties determined from unconfined compression test for cement stabilized soil aggregates of Northern Thailand. Three types of soil aggregates were used in this study: Laterite, Terrace Gravel and Decomposed Granite. The soil aggregates were mixed with cement in the range of 2 to 10 percent by weight and compacted to their maximum dry density at optimum moisture content values. The compacted cement stabilized soil samples were cured for 7 days under room temperature and moisture conditions before subjected to unconfined compression or repeated load tests. Repeated load indirect tensile and triaxial compression tests were used to determine the values of resilient modulus.

Results from unconfined compression test indicate that values of unconfined compressive strength of the different soils increase with the increases in cement contents at varying constant rates. For the Terrace Gravel and Decomposed Granite which are well graded and containing only

**(**\_

small amount of fines, the rate of increase in unconfined compressive strength with cement contents are equal with each other but higher than in case of the Laterite which is poorly graded and containing more fines. Values of elastic modulus  $E_{50}$  determined from stress – strain relationship of unconfined compression test were also found to be increasing linearly with cement contents. For the Terrace Gravel which is well graded and has low percentage of wear, the rate of increase in modulus values with cement contents was found to be highest. For the Decomposed Granite which has higher percentage of wear, the rate of increase was found to be lower than Terrace Gravel even though both soils are of almost of the same grain size distribution and plasticity. For the Laterite, the rate of increase in elastic modulus with cement contents was found to be lowest. Furthermore, it was found that elastic modulus  $E_{50}$  values show good linear correlation with unconfined compressive strength values for all type of soils. Correlations for the Laterite and the Decomposed Granite are almost unique while the linear correlation of the Terrace Gravel seems to have steeper slope.

1.1

(

Values of resilient modulus from indirect tensile test show similar trends of changes with soil properties and cement contents as those of the elastic modulus  $E_{50}$  values. Values of resilient modulus are however found to be higher than elastic modulus  $E_{50}$  values and also higher than resilient modulus values as reported by other researchers. This was thought to be due to the low stress level used in the repeated load test of this study (about 3.0 percent of unconfined compressive strength). Results of the repeated load triaxial test indicate that values of resilient modulus do not vary significantly with soil types and cement contents.

Correlations between resilient modulus from indirect tensile test and unconfined compressive strength values were found to vary for the different soil types. But a unique empirical correlation between resilient modulus and elastic modulus  $E_{50}$  values was found for all the soils used in this study. This empirical correlation,  $M_R = 21$  ( $E_{50}$ ), has coefficient of determination of 0.893 and 95 percent confidence level.