หัวซ้อการวิจัย การวิจัย ชื่อผู้ทำ ตัวต้านทานผลิตจากส่วนผสมของเชรามิคส์และผงโลหะบีสมัท วิทยาศาสตร์มหาบัญฑิต (การสอนพิสิกส์) มหาวิทยาลัยเชียงใหม่ 2521 ชะยันต์ อินเล็ก

## บทคัดยอ

การวิจัยนี้ได้สร้างเตาเผาที่ให้ความร้อนโดยใช้กระแสไฟฟ้า และสร้าง เครื่องควบคุมอุณหภูมิที่ใช้ SCR (silicon controlled rectifier) เป็นสวนประกอบ เทาเผาและเครื่องควบคุมอุณหภูมิชุดนี้สามารถให้ความร้อนไค้ถึงอุณหภูมิประม**าณ 1273** k มีความแมนยำ ±4° ห นอกจากนี้ยังไค้สร้างเครื่องปนผงโลหะและผงเซรามิคส์แบบ continuous collision การศึกษาคุณสมบัติทางไฟฟ้าของตัวตานทานที่ผลิตจากส่วน ผสมของผงโลหะบิสมัทกับผงเซรามีคล์ ในอัตราสวน 30:70,50:50,70:30 และ 90:10 เปอร์เซนต์โดยน้ำหนัก ปั้นเป็นแทงทรงกระบอกคล้ายกับตัวต้านทานที่ใช้โดยทั่วไป นำไปเผา (anneal) ที่อุญหภูมิ 1123°K เป็นเวลา 1,2,3,6,9 และ 7½ ชั่วโมง แล้ววัดคำ สภาพตานทานไฟฟ้า (resistivity) ที่อุณหภูมิตาง ๆ เพื่อศึกษาการเปลี่ยนแปลงกับ อุณหภูมิ ผลปรากฏวาคาสภาพต้านทานไฟฟ้าเปลี่ยนแปลงกับอุญหภูมิและสวนผสม การใช้ แรงปีบอัดตางกันนั้นความแตกตางของสภาพตานหานไฟฟ้าไม่อาจสังเกตได้ และค่าสภาพ ท้านทานไฟฟ้าเปลี่ยนแปลงตามเวลาเล็กน้อย กราฟของสภาพท้านทานไฟฟ้าวัคชณะเพิ่ม และลดอุณหภูมิจะทับรอยเดิมเมื่อเผาตัวต้านทานเป็นเวลาที่เหมาะสม ในการศึกษาการ นำไฟฟ้าของตัวต้านทาน ได้ศึกษาการเปลี่ยนแปลงคาสภาพต้านทานไฟฟ้ากับส่วนกลับของ อณหภูมิและได้คำนวณหา activation energy ซึ่งมีคาอยู่ในชวงประมาณ 0.182-1.967 ev โดยสมมุติวาการนำไฟฟ้าเป็นไปตามสมการซอง Arrhenius คือ  $ho = 
ho_0 \exp(rac{E}{kT})$  อยางไรก็ตาม การเคลื่อนที่พองประจุไฟฟ้า นาจะเกิดจากการกระโดด จากแถบวาเลนซ์ ไปยังแถบการนำเนื่องจากความรอน

Title Cermet Resistors (Bi)

Research Master of Science (Teaching Physics) Chiang Mai

University 1978

Name Chayan Inleck

## Abstract

In this research, an electric furnace was constructed. The temperature controller was made by using SCR (silicon controlled rectifier). The furnace could be heated and controlled to a temperature about 1273°K, to an accuracy of 4°K. A milling machine was also made to reduce the particle size of bismuth powder and ceramic clay by centinuous collision. The electrical properties of cermet resistors were studied. These resistors were made of bismuth powder and ceramic clay with ratio 30:70, 50:50, 70:30 and 90:10 percent by weight. They were made in small red shape similar to commercial resistors. The resistor was introduced into the furnace and annealed to a temperature 1123°K for 1,2,3,6,9 and 7½ hours. The resistivities were measured at various temperatures after annealing. The resistivities depend on temperature and the mixture ratio, but they do not depend on pressure in preparing, and slightly depend on ageing. The . resistivities measured when temperature was increased and decreased were reversible, if the sufficient annealing times were employed. The conduction mechanism was determined from the relationship of resistivities v.s. reciprocal temperature. The activation energy was estimated to be in the range 0.182-1.967 eV. It is assumed that the resistivities obey the Arrhenius relation  $\rho = \rho_0 \exp(\frac{E}{kT})$ . However the conduction mechanism is assumed to occur by the charge particles jumping from valence band to conduction band by thermal activation.