

**ชื่อเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ ผลของการเติมธาตุเงินต่อความหนาแน่น
กระแสไฟฟ้าติดของสารตัวนำயอดยิ่ง $YBa_2Cu_3O_{7-x}$**

ชื่อผู้เขียน

นางสาวสังสรรค์ ศิริวัฒนวิบูลย์

วิทยาศาสตรมหาบัณฑิต

สาขาวิชาการสอนพิสิเก็ต

คณะกรรมการสอบการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ :

รองศาสตราจารย์ ดร. ผ่องศรี มังกรทอง

ประธานกรรมการ

ผู้ช่วยศาสตราจารย์ ดร. ศรีเพ็ญ ท้าวตา

กรรมการ

อาจารย์อัจฉราวรรณ

ภาคเจริญ

กรรมการ

บทคัดย่อ

ศึกษาการเติม Ag_2O ลงในสารตัวนำยอดยิ่งอุณหภูมิสูง $YBa_2Cu_3O_{7-x}$ ในปริมาณของ Ag_2O ในช่วง 0 - 30 มิลเบอร์เร็นต์ ด้วยวิธีปฏิกิริยาของแข็งโดยใช้อุณหภูมิในการ sinter ที่แตกต่างกันในช่วง $920^{\circ}C$ - $970^{\circ}C$ พบร่วม สารที่เตรียมได้แสดงปรากฏการณ์เมอร์สเนอร์ทุกเม็ด จากการวัดค่าอุณหภูมิวิกฤต (T_c) ด้วยวิธี four-point probe พบร่วม มีค่าอยู่ในช่วง 79 - 96 K และวัดค่าความหนาแน่นกระแสไฟฟ้า (ρ) ด้วยวิธี pulse current technique ที่ 78 K, 0 T ได้ค่าความหนาแน่นกระแสไฟฟ้าสูงสุดเท่ากับ $1087 A/cm^2$ ที่ปริมาณของ Ag_2O เท่ากับ 5 มิลเบอร์เร็นต์ และพบว่าอุณหภูมิที่ใช้ในการเผาสารที่ให้ค่า J_c สูงในทุกสารตัวอย่างที่เตรียมมีค่าเท่ากับ $930^{\circ}C$ และจากการวิเคราะห์ผลการเลี้ยวเบนของรังสีเอกซ์ของสาร $YBa_2Cu_3O_{7-x}$ ที่เติม Ag_2O 5 มิลเบอร์เร็นต์ พบร่วม มีโครงสร้างแบบอวิโตรومบิกเพอร์อฟฟ์ไกต์ และมีพารามิเตอร์แลตทิซ $a = 3.821 \text{ \AA}$, $b = 3.892 \text{ \AA}$ และ $c = 11.689 \text{ \AA}$

Research Title Effect of Ag Doping on Critical Current Density of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$
Superconductor

Author Miss.Songsan Siriwanavibul

M.S. Teaching Physics

Examining Committee :

Assoc. Prof. Dr.Pongsri

Mangkorntong

Chairman

Assist. Prof. Dr.Sripen

Towta

Member

Instructor. Atcharawon

Gardchareon

Member

Abstract

The Ag doped $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ superconductors with mole % Ag_2O in the range of 0 - 30 have been prepared by solid state reaction using sintering temperatures from 920 to 970°C . It was found that all samples showed Meissner effect. The critical temperature (T_c) measured by the four-point probe method were 79 - 96 K. Also, the maximum value of the critical current densities (J_c) measured by the pulse current technique at 78 K and 0 T was 1087 A/cm^2 , observed in the sample with 5 mole % of Ag_2O . The optimum sintering temperature that yielded high J_c was 930°C . The crystal structure of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ with 5 mole % of Ag_2O was identified by means of x-ray diffraction to be orthorhombic, with lattice parameters $a = 3.821 \text{ \AA}$, $b = 3.892 \text{ \AA}$ and $c = 11.689 \text{ \AA}$.