

ชื่อเรื่องวิทยานิพนธ์                      ลูกบดเนื้อเซอร์โคเนียสำหรับหม้อบดเซรามิก  
ชื่อผู้เขียน                                    นางสาวเพียงใจ ศรีมหาโกศล  
วิทยาศาสตร์มหาบัณฑิต                สาขาวิชาเคมี

คณะกรรมการสอบวิทยานิพนธ์ :

รองศาสตราจารย์ ดร. กาญจนะ แก้วกำเนิด	ประธานกรรมการ
รองศาสตราจารย์ ดร. ประสัคดิ์ ฉาวฤทธิ์การต์	กรรมการ
ผู้ช่วยศาสตราจารย์ ดร. โกศล สาระเวก	กรรมการ

#### บทคัดย่อ

ได้ทำการวิจัยเพื่อหาส่วนผสมเนื้อเซอร์โคเนียที่เหมาะสม ในการทำลูกบดสำหรับหม้อบดเซรามิก โดยการนำวัตถุดิบมาร้อนผ่านตะแกรงขนาด 115 เมช แล้วนำไปบดด้วยครกไฟฟ้าประมาณ 1 ชั่วโมง นำมาขึ้นรูปแบบทรงกลมโดยการหล่อต้นและแบบทรงกระบอกโดยการอัด จากนั้นนำมาเผาพบว่า ส่วนผสมที่เหมาะสมจะประกอบด้วยเซอร์โคเนีย 90%, ดินดำแมร์ริม 2%, เบนโทไนท์ 3%, ทัลคัม 4.25%, วอลลาสโตไนท์ 0.75% และประกอบด้วยตัวช่วยทำให้เกิดการสุกตัวคือแมกนีเซียมคาร์บอเนต 5% โดยเผาที่อุณหภูมิ 1550 °ซ ในบรรยากาศออกซิเดชันจะทำให้เนื้อส่วนผสมหลังเผาแน่นตัวได้ดี มีค่าความพรุนตัวเป็นศูนย์ มีค่าความหนาแน่น 4.25 กรัม/ซม<sup>3</sup> มีความแข็ง 8-9 โมห์สเกล ทนทานต่อการสึกกร่อนค่อนข้างดี จากผลการวิเคราะห์ทางเคมีของส่วนผสมดังกล่าวนี้มีเซอร์โคเนีย 82.88%, ซิลิกา 10.02%, เหล็กออกไซด์ 0.16%, ดิเตเนียมออกไซด์ 0.01%, อลูมินา 2.67%, แคลเซียมออกไซด์ 0.17%, แมกนีเซียมออกไซด์ 3.53%, โซเดียมออกไซด์ 0.15%, โพแทสเซียมออกไซด์ 0.14% และสารที่หายไปหลังจากการเผา 0.12%

**Thesis Title**            Zirconia Grinding Ball for Ceramic Ball Mill

**Author**                    Miss Piengjai Srimahakosol

**M.S.**                        Chemistry

**Examining Committee :**

Assoc. Prof. Dr. Kanchana Keowkamnerd	Chairman
Assoc. Prof. Dr. Prasak Thavornytikarn	Member
Assist. Prof. Dr. Kosol Sarawek	Member

**Abstract**

The suitable zirconia bodies to make grinding balls for ceramic ball mill were studied. Raw materials were sieved through 115 mesh size and grinded in electrical mill for about 1 hour. The grinding balls were formed by solid casting for a spherical balls and pressed for a cylindrical balls. It was found that the best composition of the zirconia body was 90% zirconia, 2% plastic clay (Maerim), 3% bentonite, 4.25% talcum, 0.75% wallastonite and 5% magnesium carbonate. After firing at 1550 °C in oxidation atmosphere, the condensed body with zero porosity, density of 4.25 g/cm<sup>3</sup> and hardness of 8-9 in Moh's scale was obtained. It was corrosive resistance. The chemical analysis of this best body was 82.88% zirconia, 10.02% silica, 0.16% iron oxide, 0.01% titanium oxide, 2.67% alumina, 0.17% calcium oxide, 3.53% magnesium oxide, 0.15% sodium oxide, 0.14% potassium oxide and 0.12% loss on ignition.