

<b>Thesis Title</b>	Characterization of Modified Barium Titanate Powders Prepared by Catecholate Process	
<b>Author</b>	Miss Wongduan Maison	
<b>Ph.D.</b>	Chemistry	
<b>Examining Committee</b>	Assoc.Prof.Dr. Sukon Phanichphant	Chairperson
	Assoc.Prof.Dr. Prasak Thavornytikarn	Member
	Prof.Dr. Tawee Tunkasiri	Member
	Assoc.Prof.Dr. Udom Sriyotha	Member
	Prof.Dr. Robert B. Heimann	Member

### ABSTRACT

A Catecholate process has been developed for the synthesis of high purity barium titanate fine powders. The barium titanium-catechol complex,  $\text{Ba}[\text{Ti}(\text{C}_6\text{H}_4\text{O}_2)_3]$  was prepared from  $\text{TiCl}_4$ ,  $\text{C}_6\text{H}_4(\text{OH})_2$  and  $\text{BaCO}_3$ . The complex was freeze-dried and calcined for 3 hours at temperatures ranging from  $600^\circ\text{C}$  to  $1100^\circ\text{C}$ . Phase transformation and particle size of the calcined powders have been investigated as a function of calcination temperatures by X-ray diffraction (XRD) and scanning electron microscopy (SEM) techniques. It was found that  $\text{BaTiO}_3$  transformed from the cubic to the tetragonal phase and increased in particle size with increasing calcination temperature. Higher temperatures clearly favoured particle growth and the formation of large and hard agglomerates.

The  $\text{BaTiO}_3$  powders, produced by the Catecholate process, were pressed into pellet and sintered to high density at a temperature of  $1350^\circ\text{C}$  for 3 hours. Using a

combination of room-temperature XRD and SEM techniques, the effect of calcination temperature on phase and microstructure of BaTiO<sub>3</sub> ceramics were examined. It can be seen that the grain size increases with increasing calcination temperature of BaTiO<sub>3</sub> powders.

The ferroelectric to paraelectric phase transition of sintered BaTiO<sub>3</sub> was investigated from dielectric properties as dielectric constant ( $\epsilon_r$ ) and dielectric loss ( $\tan \delta$ ) as a function of temperatures. From the result of dielectric measurement, it was found that the maximum dielectric constant ( $\epsilon_r$ ) at Curie temperature ( $T_c$ ) was observed for a calcination temperature at 900°C.

The influence of dopants (Ti<sup>4+</sup>, Mn<sup>2+</sup>, Fe<sup>2+</sup>, Zr<sup>4+</sup>, Nb<sup>5+</sup>, Sb<sup>5+</sup> and Ce<sup>4+</sup>) on the crystal structure, microstructure and dielectric properties of barium titanate were studied at room temperature using X-ray diffraction, scanning electron microscopy and dielectric measurements. Fine BaTiO<sub>3</sub> powders have been doped with 1 mol% of the foreign element and sintered for 3 hours at 1350°C. The room temperature structure of doped BaTiO<sub>3</sub> in all cases was tetragonal with c/a ratio lower than in the undoped perovskite, but microstructure and dielectric properties depend on the dopant nature and particle size. In 1 mol% Ti<sup>4+</sup>-, Mn<sup>2+</sup>-, Fe<sup>2+</sup>-, and Zr<sup>4+</sup>-doped BaTiO<sub>3</sub>, grain growth developed, in contrast to Nb<sup>5+</sup>-, Sb<sup>5+</sup>-, and Ce<sup>4+</sup>-doped BaTiO<sub>3</sub> in which grain growth during sintering was inhibited. The Curie temperature ( $T_c$ ) shifts to lower values in Fe<sup>2+</sup>-, and Sb<sup>5+</sup>-doped BaTiO<sub>3</sub>. The dielectric peaks are strong and sharp for Ti<sup>4+</sup>-, Mn<sup>2+</sup>-, Fe<sup>2+</sup>-, and Zr<sup>4+</sup>-doped BaTiO<sub>3</sub>, whereas broad peaks were found for Nb<sup>5+</sup>-, Sb<sup>5+</sup>-, and Ce<sup>4+</sup>-doped BaTiO<sub>3</sub>. The highest dielectric constant ( $\epsilon_r$ ) at Curie temperature ( $T_c$ ) was found for Mn<sup>2+</sup>-doped BaTiO<sub>3</sub>.

**ชื่อเรื่องวิทยานิพนธ์** การหาลักษณะเฉพาะของผงแบเรียมดีทานเนตดัดแปลงที่เตรียม  
โดยกระบวนการแคททีคอลลิต

**ชื่อผู้เขียน** นางสาววงเดือน ไม้สนธิ์

**วิทยาศาสตร์ดุษฎีบัณฑิต** สาขาวิชาเคมี

<b>คณะกรรมการสอบวิทยานิพนธ์</b>	รศ.ดร. สุคนธ์ พานิชพันธ์	ประธานกรรมการ
	รศ.ดร. ประศักดิ์ ถาวรยุติการต์	กรรมการ
	ศ.ดร. ทวี ดันขศิริ	กรรมการ
	รศ.ดร. อุดม ศรีโยธา	กรรมการ
	ศ.ดร. โรเบิร์ต บี ไฮแมนน์	กรรมการ

### บทคัดย่อ

ผงแบเรียมดีทานเนตที่มีความบริสุทธิ์สูงสามารถเตรียมได้โดยวิธีแคททีคอลลิต สารประกอบเชิงซ้อนแบเรียมดีทานเนตแคททีคอลลิตถูกเตรียมขึ้นจากการทำปฏิกิริยาระหว่างดีทานเนตเตตระคลอไรด์ แคททีคอลลิต และแบเรียมคาร์บอเนต นำสารประกอบเชิงซ้อนที่ได้มาทำการฟริชทรายและแคลไซน์ที่อุณหภูมิระหว่าง  $600-1100^{\circ}\text{C}$  เป็นเวลา 3 ชั่วโมง เทคนิคการเลี้ยวเบนรังสีเอกซ์ (XRD) และกล้องจุลทรรศน์อิเล็กตรอนแบบส่องกราด (SEM) ใช้ศึกษาการเปลี่ยนแปลงเฟสและขนาดอนุภาคของผงแบเรียมดีทานเนตที่เตรียมได้ ผลการทดลองพบว่า เมื่อเพิ่มอุณหภูมิแคลไซน์มีการเปลี่ยนแปลงเฟสของผงแบเรียม ดีทานเนตจาก cubic ไปเป็น tetragonal และมีการเพิ่มของขนาดอนุภาค โดยที่อนุภาคจะมีขนาดใหญ่ขึ้นและเกาะกันเป็นกลุ่มก้อน เมื่อเพิ่มอุณหภูมิแคลไซน์

ผงแบเรียมดีทานเนตที่เตรียมได้ นำมาขึ้นรูปโดยอัดเป็นเม็ด แล้วทำการเผาซินเตอร์ พบว่าให้ค่าความหนาแน่นสูงสุดที่อุณหภูมิเผาซินเตอร์  $1350^{\circ}\text{C}$  นาน 3 ชั่วโมง ผลของอุณหภูมิแคลไซน์ต่อการเปลี่ยนแปลงเฟส และโครงสร้างทางจุลภาคของแบเรียมดีทานเนตเซรามิก สามารถตรวจสอบได้โดยใช้เทคนิค XRD และ SEM พบว่าเมื่อเพิ่มอุณหภูมิแคลไซน์แต่อุณหภูมิเผาซินเตอร์เดียวกันขนาดของเกรน มีลักษณะโคขึ้น

การเปลี่ยนแปลงเฟสของแบเรียมดีทานเตเซรามิกจากเฟอโรอิเล็กทริกไปเป็นพาราอิเล็กทริก ตรวจสอบได้จากสมบัติไดอิเล็กทริก ได้แก่ ค่าคงที่ไดอิเล็กทริก ( $\epsilon_r$ ) และค่าการสูญเสียทางไดอิเล็กทริกเทียบกับอุณหภูมิ พบว่าที่อุณหภูมิเคลวิน 900 $^{\circ}$ C ให้ค่าคงที่ไดอิเล็กทริกสูงสุด

ทำการตรวจสอบลักษณะโครงสร้างผลึก โครงสร้างทางจุลภาค และสมบัติไดอิเล็กทริกของแบเรียม ดีทานเตเซรามิก เมื่อมีการเติม 1 โมล% ของตัวโคป เช่น ดีทานเนียม แมงกานีส เหล็ก เซอร์โคเนียม ในโอเบียม แอนติโมนี และ ซีเรียม โดยทำการเผาซินเตอร์ที่อุณหภูมิ 1350 $^{\circ}$ C นาน 3 ชั่วโมง พบว่า แบเรียมดีทานเตเซรามิกที่มีการเติมตัวโคป มีลักษณะโครงสร้างผลึกเป็นแบบ tetragonal โดยมีค่าอัตราส่วนระหว่าง  $c/a$  ต่ำกว่าแบเรียมดีทานเตเซรามิกก่อนที่มีการเติมตัวโคป ส่วนลักษณะโครงสร้างทางจุลภาค และสมบัติไดอิเล็กทริกขึ้นอยู่กับธรรมชาติและขนาดอนุภาคของสารที่ใช้ในการโคป แบเรียมดีทานเตที่มีการโคปด้วย ดีทานเนียม แมงกานีส เหล็ก และ เซอร์โคเนียม จะทำให้ขนาดของเกรนโตขึ้น ในขณะที่การโคปด้วย ในโอเบียม แอนติโมนี และ ซีเรียม จะไปยับยั้งการเจริญเติบโตของเกรน ส่วนสมบัติไดอิเล็กทริก พบว่า การโคปด้วย เหล็ก และ แอนติโมนี มีผลทำให้อุณหภูมิคูรี ( $T_c$ ) เลื่อนต่ำลง พิกของค่าคงที่ไดอิเล็กทริกจะแคบเมื่อมีการโคปด้วย ดีทานเนียม แมงกานีส เหล็ก และ เซอร์โคเนียม ในขณะที่พิกจะกว้างเมื่อโคปด้วย ในโอเบียม แอนติโมนี และ ซีเรียม จากผลการทดลองที่ได้พบว่าแบเรียมดีทานเตที่มีการโคปแมงกานีส จะให้ค่าคงที่ไดอิเล็กทริก ( $\epsilon_r$ ) สูงสุดที่อุณหภูมิคูรี ( $T_c$ )