

ชื่อเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ การวิเคราะห์ทางเคมีของเครื่องปั้นดินเผา
ชนิดเคลือบสันกำแพง

ชื่อผู้เขียน

นางสาวเริงฤกษ์ ประทุมโภน

วิทยาศาสตรมหาบัณฑิต

สาขาวิชาการสอนเคมี

คณะกรรมการตรวจสอบการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ :

รศ. ดร. ประศักดิ์

ดาวรยุติการต์

ประธานกรรมการ

รศ. ดร. กานุจนา

แก้วกำเนิด

กรรมการ

อ. ดร. มงคล

รายงานการ

กรรมการ

นักศึกษา

ได้ทำการวิเคราะห์ทางเคมีของเนื้อดินปั้นและเคลือบของเครื่องปั้นดินเผาชนิดเคลือบสันกำแพงหาชิลิกาและอลูมีนา โดยวิธีการตกลงก่อน ติเตเนียมออกไซด์โดยวิธีเทียนสีเหล็กออกไซด์โดยใช้ใจนลร์ดัคเตอร์ สำหรับออกไซด์ของแคลเซียม, แมกนีเซียม, โซเดียม และ ไบต์สเซี่ยมaha โดยวิธีของคอมมิกแอนชันชั่นสเปค โทร.ไฟโตเมตรี พบว่าเนื้อดินปั้นมีปริมาณของชิลิกาอยู่ในช่วง 70-77 %, อลูมีนา 16-21 %, ติเตเนียมออกไซด์ 0.03-0.6 %, เหล็กออกไซด์ 1.4-3.0 %, แคลเซียมออกไซด์ 0-0.1 %, แมกนีเซียมออกไซด์ 0.2-0.7 %, โซเดียมออกไซด์ 0.3-0.7 % และ ไบต์สเซี่ยมออกไซด์ 3.5-6.6 % สำหรับในเคลือบจะพบปริมาณของชิลิกาอยู่ในช่วง 55-65 %, อลูมีนา 16-19 %, ติเตเนียมออกไซด์ 0.4-0.6 %, เหล็กออกไซด์ 1.0-1.5 %, แคลเซียมออกไซด์ 6-14 %, แมกนีเซียมออกไซด์ 1.2-2.3 %, โซเดียมออกไซด์ 0.2-1.9 % และ ไบต์สเซี่ยมออกไซด์ 3.2-6.7 %

Research Title Chemical Analysis of Sankampaeng Glazed Pottery

Author Ms.Rerngnaporn Pratumtong

M.S. Teaching Chemistry

Examining Committee :

Assoc.Prof.Dr.Prasak	Thavornyutikarn	Chairman
----------------------	-----------------	----------

Assoc.Prof.Dr.Kanchana	Keowkamnerd	Member
------------------------	-------------	--------

Lecturer Dr.Mongkon	Rayanakorn	Member
---------------------	------------	--------

Abstract

Chemical analysis of the bodies and glazes of some Sankampaeng glazed pottery was carried out. Gravimetric method was used to determine silica and alumina. Titanium oxide was analysed by colorimetry. Iron oxide was analysed by Jones reductor method ; oxides of calcium, magnesium, sodium and potassium were analysed by atomic absorption spectrophotometry. It was found that the composition of the bodies was in the ranges of 70-77 % silica, 16-21 % alumina, 0.03-0.6 % titanium oxide, 1.4-3.0 % iron oxide, 0-0.1 % calcium oxide, 0.2-0.7 % magnesium oxide, 0.3-0.7 % sodium oxide and 3.5-6.6 % potassium oxide. The composition of the glazes was in the ranges of 55-65 % silica, 16-19 % alumina, 0.4-0.6 % titanium oxide, 1.0-1.5 % iron oxide, 6-14 % calcium oxide, 1.2-2.3 % magnesium oxide, 0.2-1.9 % sodium oxide and 3.2-6.7 % potassium oxide.