

**ชื่อเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ การศึกษาดินปืนและเคลือบสำหรับ  
ผลิตภัณฑ์ไฟฟ้าโดยใช้วัตถุตินบางชนิดของห้องถังภาคเหนือ  
ของประเทศไทย**

**ชื่อผู้เขียน**

**นายสมชาย ล้มพันธุ์วิวัฒน์**

**วิทยาศาสตรมหาบัณฑิต สาขาวารสันด์เมือง**

**คณะกรรมการตรวจสอบการค้นคว้าแบบอิสระ: เชิงวิทยานิพนธ์**

**รศ.ดร. กานุจนา แก้วกำเนิด**

**ประธานกรรมการ**

**รศ.ดร. ประศักดิ์ ถาวรยุติกรต์**

**กรรมการ**

**นายสุรพล ตันน้ำแสง**

**กรรมการ**

**บทคัดย่อ**

ได้ทำการศึกษาการทำผลิตภัณฑ์เอทเทนชันด์เพาไฟฟ้า โดยการใช้วัตถุติน  
ทางภาคเหนือของประเทศไทย ได้แก่ ตินหางดง เชียงใหม่ ตินห้างฉัตรล้ำปาง  
ตินลิกไนท์ ล้ำปาง ตินซีริไซท์ อุตรดิตถ์ และตินໄไดอะกอยไมท์ เกาะคา ล้ำปาง  
ศึกษาส่วนผสมเนื้อตินปืน โดยแผนผังสามเหลี่ยมแสดงอัตราส่วนผสม จากการทดลอง  
พบว่า สมบัติที่ต้องเนื้อตินปืน เมื่อเผาที่อุณหภูมิ 1100-1200 องศาเซลเซียล  
บรรยายกาศออกซิเตชัน มีเนื้อตินปืนหางดง 10 ชนิด ตินห้างฉัตร 5 ชนิด ตินลิกไนท์  
5 ชนิด ตินซีริไซท์ 2 ชนิด และตินໄไดอะกอยไมท์ 2 ชนิด พิจารณาดูเนื้อตินปืนที่ต้อง  
หลังการเผาโดยคุณลักษณะเนื้อติน และการทดสอบ สุกห้ำยเลือกได้เนื้อตินปืนที่ต้องสุดของ  
แต่ละแพกเกจ ยกเว้นเนื้อตินปืนอันสุดห้ำย เนื้อตินปืนหางดง ประกอบด้วย ติน  
หางดง 60% ตินล้ำปาง 30% และตินซีริไซท์ 10% เนื้อตินปืนห้างฉัตรประกอบด้วย  
ตินห้างฉัตร 60% และตินแมร์ริม 40%, เนื้อตินปืนลิกไนท์ประกอบด้วย ตินลิกไนท์  
40% หินล้ำปาง 40% และไอกอยไมท์ 20%, เนื้อตินปืนซีริไซท์ ประกอบด้วย  
ตินซีริไซท์ 50% ตินแมร์ริม 40% และตินเกอลิน เวียงป่าเป้า 10% สมบัติเนื้อตินปืน  
ที่ต้องสามารถนำมาขึ้นรูปทำผลิตภัณฑ์ได้และสามารถรวมกับน้ำเคลือบได้หลายชนิด เช่น  
เคลือบสี มีสีขาว เหลือง เขียว ฟ้า น้ำเงิน เขียวอมดำ ดำ และยังนำไปร่วมกับหิน  
เป็นสารให้สีได้ เช่น ไฟโรลูไซท์ อิลเมไนท์ และโคโรไมท์ และยังได้ใช้เคลือบ  
มากกว่า เคลือบไม่ใส่มากกว่า เคลือบฟริต และเคลือบพิเศษ เช่น น้ำเคลือบสีทอง  
น้ำเคลือบสีน้ำเงินมากที่

Research Title      A Study of Body and Glaze for Low Fired  
Temperature Product Using Some Local  
Raw Materials in Northern Thailand

Author                Mr. Somchai Sumphunvivatana

M.S.                 Teaching Chemistry

Examining Committee :

Assoc. Prof. Dr. Kanchana Keowkamnerd      Chairman

Assoc. Prof. Dr. Prasak Thavornyutikarn      Member

Mr. Surapon Thannumsaeng      Member

### Abstract

Low temperature earthenware products using some raw materials in Northern Thailand was studied. The main raw materials were Hang Dong clay, Chiangmai, Hangchat clay, Lampang, lignite clay, Lampang, sericite, Uttaradit and diatomite clay, Koh-Ka, Lampang. The mixtures of clay bodies were systematically studied by triaxial, it was found that good bodies were fired at 1100-1200 °C in oxidation atmosphere. 10 Composition of Hang Dong clay bodies, 5 composition of Hangchat bodies, 5 composition lignite clay bodies, 2 composition sericite clay bodies and 2 kinds of diatomite bodies were obtained. The properties of fired test pieces such as color appearance and shrinkage were considered for best bodies. Finally, the best bodies were

selected from each pattern except the last one. The composition of Hang Dong body was 60% Hang Dong clay, 30% Lampang clay and 10% sericite clay; Hangchat body, 60% Hangchat clay and 40% Maerim clay; lignite body, 40% lignite clay, 40% Lampang stone and 20% diatomite; sericite body, 50% sericite clay, 40% Maerim clay and 10% kaolin, Vieng-pa-pao. The clay bodies could be used to form products without difficulty and they were fitted for various glazes: such as colored glazes; white, yellow, green, sky blue, violet, gold, blue, dark green and black; some minerals such as pyrolusite, ilmenite and chromite, were used as colourants, lead glaze, leadless glaze, frit glaze and special glaze; gold luster glaze and emerald blue glaze.