

ชื่อเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ เคลือบเหล็กชนิดเทม โนกุสำหรับผลิตภัณฑ์ สโต้แวร์

ชื่อผู้เขียน

นางสาวชนิษฐา สุวรรณลักษิต

วิทยาศาสตร์มหาบัณฑิต

สาขาวิชาการสอนเคมี

คณะกรรมการสอบการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์ :

รองศาสตราจารย์ ดร. กาญจน์ แก้วกำเนิด

รองศาสตราจารย์ ดร. ประศักดิ์ ถาวรยุติการ์ต

ผู้ช่วยศาสตราจารย์ ดร. โภศล สาระเวก

ประธานกรรมการ

กรรมการ

กรรมการ

### บทคัดย่อ

ได้ศึกษาการเคลือบเหล็กชนิดเทม โนกุ สำหรับผลิตภัณฑ์สโต้แวร์พบว่า เคลือบที่  
เหมาะสม ให้ลักษณะ เคลือบเทม โนกุที่ปราศจากเส้นคล้ายขันสีตัววีคือ เคลือบที่มีลักษณะสมประกอบด้วย  
เฟลสปาร์ 23.33% แคลเซียมคาร์บอเนต 17.47% ควอทซ์ 28.84% ดินกอกอไชร์ 1.40% ดิน  
ด้ำเมริม 4.69% ตะกั่วขาว 3.52% กำมะถัน 3.52% และเหล็กออกไซด์ 17.23% โดย  
เพาท์อุณหภูมิ  $1320^{\circ}\text{C}$  (เอกสาร เค.11) ในบรรยายการศึกษาเดือน และเคลือบเทม โนกุที่ให้จุด  
คงดองคงคล้ายหยดน้ำมัน คือเคลือบที่มีลักษณะสม เคลือบประกอบด้วย เฟลสปาร์ 89.00% แคลเซียม  
คาร์บอเนต 4.00% เหล็กออกไซด์ 6.00% แมงกานีสต์ออกไซด์ 0.50% และโคบล็อดออกไซด์  
0.50% โดยเพาท์อุณหภูมิ  $1280^{\circ}\text{C}$  (เอกสาร เค.9) ในบรรยายการศึกษาเดือน การเพาเคลือบ  
ทึบสองจะแข็งในประมาณ 30 นาที ใช้เวลาเพาทึบลีบประมาณ 10 - 12 ชั่วโมง

Research Title      Temmoku Iron Glaze for Stoneware

Author                Ms. Khaniththa Suwonlikhit

M.S.                 Teaching Chemistry

Examining Committee :

Assoc. Prof. Dr. Kanchana Keowkamnerd      Chairman

Assoc. Prof. Dr. Prasak      Thavornyutikarn Member

Assist. Prof. Dr. Kosol      Sarawek Member

### Abstract

Temmoku iron glaze for stoneware products were studied. It was found that the most suitable fur-like temmoku glaze was 23.33% feldspar, 17.47% calcium carbonate, 28.84% quartz, 1.40% tin oxide, 4.69% Maerim plastic clay, 3.52% white lead, 3.52% sulfur and 17.23% iron oxide. This glaze has a vitreous point at 1320°C (SK.11) by oxidation firing. The most suitable oil spot temmoku was 89.00% feldspar, 4.00% calcium carbonate, 6.00% iron oxide, 0.50% maganese oxide and 0.50% cobalt oxide. This glaze has a vitreous point at 1280°C (SK.9) by oxidation firing. At the final temperature, both glazes were soaked approximately 30 minutes. The firing time of these glazes was about 10-12 hours.