

ชื่อเรื่อง การศึกษาการกำจัดกำมะถันในด้านหินลิกไนต์ อาร์เกอส์ ด้วยสารละลายโซเดียมคาร์บอนเนต

ชื่อผู้เขียน ยุทธนา สุทธิพงศ์

การค้นคว้าแบบอิสระ เชิงวิทยานิพนธ์ วิทยาศาสตรมหาบัณฑิต สาขาวิชาการสอนเคมี มหาวิทยาลัยเชียงใหม่ 2527

บทคัดย่อ

กำมะถันในด้านหิน เป็นองค์ประกอบที่ทำให้เกิดการกัดกร่อนและเกิดมลพิษ การกำจัดกำมะถันในด้านหินลิกไนต์ 4 ขนาด คือ ขนาด 0 - 0.50 มิลลิเมตร, 0.50 - 1.00 มิลลิเมตร, 1.00 - 2.00 มิลลิเมตร และ 2.00 - 4.75 มิลลิเมตร จากแหล่งบ้านปู และบ้านป่าค่า อาร์เกอส์ จังหวัดลำพูน โดยใช้สารละลายโซเดียมคาร์บอนเนตที่ร่อน และมีออกซิเจนละลายอยู่ด้วย ที่อุณหภูมิ 150 ° ซ ความดัน 160 ปอนด์/ตารางนิ้ว พบร้า เมื่อใช้สารละลายโซเดียมคาร์บอนเนตเข้มข้น รอยละ 1.0 โดยน้ำหนัก ในเวลา 1 ชั่วโมง ด้านหินขนาดเล็กถูกกำจัดกำมะถันได้ที่สุด การกำจัดกำมะถันของด้านหินเหลงบ้านปู และบ้านป่า ขนาด 0 - 0.50 มิลลิเมตร ปริมาณไฟฟ์ติกซัลเฟอร์คลอร์ รอยละ 29.87 และ 26.81 โดยน้ำหนัก ชัลเฟต์ซัลเฟอร์คลอร์ รอยละ 73.35 และ 68.73 โดยน้ำหนัก ขณะที่ค่าความร้อนลดคลลง รอยละ 2.07 และ 2.02 โดยน้ำหนัก แคปริเมตเติลเพิมชัน รอยละ 5.90 และ 5.85 ตามลำดับ

Research Title The Study on Desulfurization of Lignite from Amphoe Li with Sodium Carbonate Solutions

Name Yuthana Suthipong

Research For Master of Science in Teaching Chemistry
Chiang Mai University 1984

Abstract

Sulfur is an impurity present in coal. It is a source of corrosion and pollution. The desulfurization of lignite of four particle size ranges : 0 - 0.50 mm, 0.50 - 1.00 mm, 1.00 - 2.00 mm and 2.00 - 4.75 mm, from Ban Pu and Ban Paka, Amphoe Li, Lamphoon Province was studied. The treatment was carried out with a hot solution of sodium carbonate at a reaction temperature of 150°C in the presence of oxygen gas under a pressure of 160 psi. It was found that the best results were obtained from a one hour treatment of a small particle size lignite in a one percent by weight sodium carbonate solution. The treated lignites from Ban Pu and Ban Paka, of size range 0 - 0.50 mm, showed that the reduction by weight of pyritic sulfur was 29.87 % and 26.81 %, that of sulfate sulfur was 73.35 % and 68.73 %, while the reduction in heating values were 2.07 % and 2.02 % respectively; however, the ash increased by 5.90 % and 5.85 % respectively.