

ชื่อเรื่องวิทยานิพนธ์

กำลังแรงยึดแบบเฉือนและลักษณะความล้มเหลวของระบบเซลเอชซิงแอดฮีซีฟสามชนิดในการยึดแบรคเกตทางทันตกรรมจัดฟัน

ผู้เขียน

นางสาวรัชมีจันทร์ กীরดีสุขสกุล

ปริญญา

วิทยาศาสตร์มหาบัณฑิต (ทันตกรรมจัดฟัน)

คณะกรรมการที่ปรึกษาวิทยานิพนธ์

รศ.วิรัช พัฒนาการณ์

ประธานกรรมการ

ผศ.ปิยะนารถ จาติเกตุ

กรรมการ

บทคัดย่อ

การศึกษานี้มีวัตถุประสงค์เพื่อหาค่าและเปรียบเทียบกำลังแรงยึดแบบเฉือนและลักษณะความล้มเหลวระหว่างระบบเซลเอชซิงแอดฮีซีฟสามชนิดกับระบบเดิมที่ใช้กรดฟอสฟอริกเอชซิงแอดฮีซีฟในการยึดแบรคเกตทางทันตกรรมจัดฟัน ลักษณะความล้มเหลวจะถูกประเมินจากตำแหน่งความล้มเหลวและจำนวนของแอดฮีซีฟที่เหลือนบนผิวเคลือบฟันภายหลังการถอดแบรคเกต กลุ่มตัวอย่างที่ใช้ในการศึกษา ได้แก่ ฟันกรามน้อยบนและล่างจำนวน 128 ซี่ที่ถูกถอนเนื่องจากการรักษาทางทันตกรรมจัดฟันจากผู้ป่วยจำนวน 32 คนที่มีอายุระหว่าง 12-19 ปี ตัวอย่างทั้งหมดจะถูกแบ่งเป็น 4 กลุ่ม กลุ่มละ 32 ซี่ โดยการสุ่มสมบรูณ์แบบบล็อก การยึดแบรคเกตให้ติดกับผิวเคลือบฟัน กลุ่มควบคุมใช้ระบบกรดฟอสฟอริกเอชซิงแอดฮีซีฟ สามกลุ่มทดลองใช้ระบบเซลเอชซิงแอดฮีซีฟสามชนิด ได้แก่ ซีโนทรี, เอดไพร์เมอร์และแอดฮีซีซี ตามลำดับ ค่าเฉลี่ยกำลังแรงยึดแบบเฉือนของกลุ่มควบคุมและสามกลุ่มทดลอง เท่ากับ 9.45, 1.48, 3.98 และ 1.74 แมกกะพาสคาลตามลำดับ โดยสามกลุ่มทดลองมีค่าเฉลี่ยกำลังแรงยึดแบบเฉือนต่ำกว่ากลุ่มควบคุมอย่างมีนัยสำคัญทางสถิติที่ระดับ 0.001 ตำแหน่งความล้มเหลวของทุกกลุ่ม ส่วนใหญ่อยู่ที่ผิวสัมผัสระหว่างแอดฮีซีฟกับฟัน และไม่พบตำแหน่งความล้มเหลวภายในผิวเคลือบฟันหรือภายในแบรคเกต กลุ่มซีโนทรีพบตำแหน่งความล้มเหลวที่ผิวสัมผัสระหว่างแอดฮีซีฟกับฟันมากกว่ากลุ่มเอดไพร์เมอร์และกลุ่มควบคุมอย่างมีนัยสำคัญทางสถิติที่ระดับน้อยกว่า 0.001

และเท่ากับ 0.001 ตามลำดับ ค่าเฉลี่ยลำดับของจำนวนของแอดฮีซีฟที่เหลือบนผิวเคลือบฟัน
ภายหลังการดื่งแบรกกะตออกจากฟันของกลุ่มควบคุมและสามกลุ่มทดลอง เท่ากับ 84.89,
41.33, 78.09 และ 53.69 ตามลำดับ กลุ่มควบคุมมีจำนวนของแอดฮีซีฟที่เหลือบนผิวเคลือบฟัน
มากกว่ากลุ่มซีโนทรีและกลุ่มแอดฮีซีฟอย่างมีนัยสำคัญทางสถิติที่ระดับน้อยกว่า 0.001 และ
เท่ากับ 0.001 ตามลำดับ กลุ่มเอดไพโรเมอร์มีจำนวนของแอดฮีซีฟที่เหลือบนผิวเคลือบฟัน
มากกว่ากลุ่มซีโนทรีและกลุ่มแอดฮีซีฟอย่างมีนัยสำคัญทางสถิติที่ระดับน้อยกว่า 0.001 และ
เท่ากับ 0.008 ตามลำดับ




ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่
Copyright © by Chiang Mai University
All rights reserved

Thesis Title	Shear Bond Strengths and Failure Modes of Three Self-Etching Adhesive Systems in Orthodontic Bracket Placement	
Author	Miss Russameejan Keratisuksakul	
Degree	Master of Science (Orthodontics)	
Thesis Advisory Committee	Assoc. Prof. Virush Patanaporn	Chairperson
	Assist. Prof. Piyanart Chatiketu	Member

ABSTRACT

The purposes of this study were to determine and compare both the shear bond strengths and the failure modes among three self-etching and one conventional phosphoric acid etching adhesive systems in orthodontic bracket placement. The failure modes were assessed from the failure sites and the amount of residual adhesives on debonded enamel surfaces after debonding. The samples in this study were 128 maxillary and mandibular premolars extracted for orthodontic reasons from 32 patients, (age range 12-19 years). All samples were divided into four groups of 32 teeth each, by completely randomized block design. Brackets in the control group were bonded to the enamel surface, using the conventional phosphoric etching adhesive system. In the three experimental groups three self-etching adhesive systems, Xeno[®] III, ED PRIMER[®] and AdheSE[®] respectively, were used. Mean shear bond strengths of the control and three experimental groups were 9.45, 1.48, 3.98 and 1.74 MPa respectively. The three experimental groups had lower mean shear bond strengths than did the control group ($p < 0.001$). Failure sites of all groups were mostly found at the adhesive/enamel interface, and were not found within enamel or

within brackets. The Xeno[®] III group had more failure sites at the adhesive/enamel interface than did the ED PRIMER[®] and control groups ($p < 0.001$, $p = 0.001$). The Mean rank of the amount of residual adhesives on debonded enamel surfaces after debonding of the control and three experimental groups were 84.89, 41.33, 78.09 and 53.69 respectively. The control group had greater amounts of residual adhesives on debonded enamel surfaces than did the Xeno[®] III and AdheSE[®] groups ($p < 0.001$, $p = 0.001$). The ED PRIMER[®] group had greater amounts of residual adhesives than those two groups ($p < 0.001$, $p = 0.008$).



ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่
Copyright © by Chiang Mai University
All rights reserved