

ชื่อเรื่องวิทยานิพนธ์	การวิเคราะห์ขนาดของบ่อวัสดุหลอมเหลวในชิ้นงานโลหะ โดยพลักซ์ความร้อนอุณหภูมิสูงเคลื่อนที่เข้าใกล้ส่วนขอบมุม อิสระของชิ้นงาน
ผู้เขียน	นายชนกันต์ จาตุรชาติ
ปริญญา	วิศวกรรมศาสตรมหาบัณฑิต (วิศวกรรมเครื่องกล)
อาจารย์ที่ปรึกษาวิทยานิพนธ์	อ.ดร.พฤกษ์ อักกะรังสี

บทคัดย่อ

ในการผลิตชิ้นงานที่มีการใช้แหล่งความร้อนเคลื่อนที่พลังงานสูง เช่นงานเชื่อม/งานตัดด้วยลำแสงเลเซอร์หรือลำแสงอิเล็กตรอน โดยเฉพาะในการผลิตเร่งด่วนแบบเพิ่มวัสดุ (Additive Rapid Manufacturing) ต้องมีตัวแปรสำคัญที่ต้องควบคุมคือขนาดของบ่อวัสดุหลอมเหลว (Melt Pool Size หรือ Weld Pool หากใช้ในงานเชื่อม) ซึ่งการควบคุมความสม่ำเสมอของบ่อวัสดุหลอมเหลวเป็นปัจจัยที่สำคัญที่มีผลกระทบต่อคุณภาพ ความเที่ยงตรงและความสม่ำเสมอของชิ้นงาน จากกระบวนการผลิตเนื่องจากคุณสมบัติของกระบวนการหน่วงเวลาทางความร้อน (Thermal Delay) ในบริเวณขอบอิสระทำให้ไม่สามารถควบคุมความสม่ำเสมอของขนาดบ่อวัสดุหลอมเหลวได้ทันทั่วทั้งที่ จึงจำเป็นต้องมีการกำหนดการเปลี่ยนแปลงตัวแปรของกระบวนการล่วงหน้าไว้ ทำให้งานวิจัยนี้มุ่งเน้นที่จะศึกษาพฤติกรรมของการเปลี่ยนแปลงขนาดของบ่อวัสดุหลอมเหลวในขณะที่แหล่งความร้อนเคลื่อนที่เข้าใกล้ขอบอิสระของชิ้นงานโลหะ AISI 304 โดยใช้การวิเคราะห์ด้วยระเบียบวิธีทางไฟไนต์เอลิเมนต์เพื่อศึกษาและรวบรวมพฤติกรรมขนาดบ่อวัสดุหลอมเหลวในบริเวณขอบอิสระซึ่งได้รับการสอบเทียบผลการวิเคราะห์กับการทดลองในกรณีที่ให้พลักซ์ความร้อนพลังงานสูงที่ตำแหน่งคงที่และในกรณีที่ให้พลักซ์ความร้อนเคลื่อนที่ด้วยความเร็วคงที่

จากผลการสอบเทียบพบว่ามีความสัมพันธ์การรับพลังงานความร้อนแตกต่างกันตามชนิดของวัสดุและอัตราพลังงานในการให้พลังงานความร้อนมีค่าอยู่ในช่วง 0.39-0.59 และผลการสอบเทียบยังสามารถบ่งชี้ว่าการวิเคราะห์ด้วยระเบียบวิธีทางไฟไนต์เอลิเมนต์สามารถใช้วิเคราะห์พฤติกรรมของการเปลี่ยนแปลงขนาดของบ่อวัสดุหลอมเหลวได้อย่างถูกต้องและสอดคล้องกับสภาพความเป็นจริงเมื่อกำหนดให้สัมพันธ์การรับพลังงานความร้อนและสภาวะเงื่อนไขมีความเหมาะสม และใช้แบบจำลองทางไฟไนต์เอลิเมนต์ศึกษาพฤติกรรมของการเปลี่ยนแปลงขนาดบ่อวัสดุ

ห ลอมเหลวไค้บรเณขอบอสรปะบว่า การเปล่ยนเปล่งขนาดของบ่อว้ศุห ลอมเหลวมเ่งขนาด
เปล่งข้ยนในลค้ษณะเปล่งเส่น โค้งเอ้กซ์โพเนนเชยลหงยรวมท้่งสามารถสร้งสมการควมส้มพ้ันช้
ระหว่งการเปล่ยนเปล่งขนาดของบ่อว้ศุห ลอมเหลวในลค้ษณะของกลุ่ต้วแปรไร้มดเ้เพื่อ่นำ
สมการไปใช้ท่นายพดค้กรรมของขนาดบ่อว้ศุห ลอมเหลวขณะท้่งแหล่งควมร้อนเคล่ยนท้่งเ้เข้าไค้
ขอบอสรปะท้่งครอบคลุ่มว้ศุห ลอชนดและมีสภาวะการผลลทหลายระดบได้ โดยมควมศดพลาค
สูงศดไม่เก่นร้อยลละ 10.5 และได้เสนอแนวท่งในการปรบเปล่ยนต้วแปรของกระบว่นการเพื่อ
ควมคุมขนาดบ่อว้ศุห ลอมเหลวในบรเณไค้ขอบอสรปะให้มขนาดสม่่าเสมอ โดยการปรบลด
อ้ตราพลังงนและเปล่งควมเร็วในการเคล่ยนท้่งรวมกัน ท้่งจะท้่งให้สามารถควมคุมขนาดของบ่อ
ว้ศุห ลอมเหลวให้ลค้ลงได้ถ้ถึงร้อยลละ 48 เมื่อกะบว่นการท้่งไม่มการควมคุม

ลค้ษลค้กรบมหาวค้ทยาล้ยเชยงใหม่
Copyright© by Chiang Mai University
All rights reserved

Thesis Title	Melt Pool Size Analysis of Metal Part with High Temperature Heat Flux Approaching a Free Edge
Author	Mr.Chanakan Jaturachat
Degree	Master of Engineering (Mechanical Engineering)
Thesis Advisor	Lect. Dr. Pruk Aggarangsi

ABSTRACT

In laser- and plasma-based additive manufacturing, cutting processes concern a high energy heat source moving across and melting metal substrates. The area of the molten material, termed melt pool or weld pool in welding process, is an essential parameter which directly influence the precision of the final products. In such manufacturing processes, feedback control systems via thermal imaging or other temperature reading schemes are commonly used to effectively control the size of melt pool during a quasi-steady state heat transfer process. Significant problems arise when the heat flux is moving towards a free edge of the feature where melt pool area drastically and rapidly increases due to heat balance disturbance. Previous works have found that feedback control mechanism is not sufficient to maintain melt pool size due to a thermal response delay.

This work focuses on the prediction of melt pool behavior near a free edge and methodologies to pre-adjust key process parameters before changes can be detected by sensors in order to achieve minimum changes in melt pool size. The approach of the work is to use a verified two-dimensional thin-walled shape finite element model to simulate the processes. The

main tasks include model verifications, melt pool behavior analyses and melt pool pre-adjust methodologies. Model verifications are carried out by comparing temperature distributions from FEM models with actual temperature during steady-state experiments and thus determine heat absorption coefficient for particular processes. Results show that coefficients of heat absorption lie between 0.39-0.59 for the concerned processes. The verified FEM model is then used to investigate transient melt pool behavior in the case that the heat source is moving across to a free edge. The results show that melt pool size increase exponentially with the distance towards the free edge. Results are presented in terms of non-dimensional parameters for the application of a broader range of processes. The representative equation returns maximum 10.5% error in melt pool size predictions near a free edge. Moreover, various operating parameters pre-adjustment scheme were attempted to minimize the effects of free edge to melt pool size increases. It is found that a combination of exponentially power decrease with linear velocity increase can reduce final melt pool size by 48% compared with constant power and velocity cases.