

Thesis Title	Growth and Application of Tin Oxide Nanowires		
Author	Mr. Suvit Thanasanvorakun		
Degree	Doctor of Philosophy (Physics)		
Thesis Advisory Committee	Dr. Atcharawon Gardchareon	Chairperson	
	Assoc. Prof. Dr. Nikorn Mangkorntong	Member	
	Assoc. Prof. Dr. Pongsri Mangkorntong	Member	
	Asst. Prof. Dr. Supab Choopun	Member	

ABSTRACT

In this research, SnO₂ nanowires have been grown by a carbothermal reduction process from the powder mixture of SnO or SnO₂ and C at synthesis temperatures in the range of 700 - 900 °C. The optimal temperature was found to be 850 °C with nanowires of several μm in length. Then, their physical properties were characterized, employing an X-ray diffractometer (XRD), an Energy Dispersive X-ray Spectrometer (EDS), Electron Microscope (SEM and TEM) and a Raman spectrometer. From XRD results it was revealed that the wires had a tetragonal rutile structure with the lattice parameters of $a = b = 4.746 \text{ \AA}$ and $c = 3.182 \text{ \AA}$. The atomic ratio of Sn and O of about 1:2 was obtained by EDS. Selected area electron diffraction from a TEM image showed that these nanowires were single crystal with the growth direction in [101]. Raman active modes of the nanowires were at 475, 634.6 and 772.5 cm⁻¹, in agreement with the values observed in the SnO₂ powder

sample. Electrical measurement of a single nanowire indicated that its conductivity at room temperature was about $4.8 (\Omega \cdot \text{cm})^{-1}$. SnO_2 nanowires were then employed for an ethanol sensor. The ethanol sensing characteristics of SnO_2 nanowires was observed from its resistance change when the sensor was exposed to ethanol vapor at concentrations in the range of 100 – 1000 ppm and heating temperature between 200 - 320 °C. The highest sensitivity of about 54 at 280 °C was observed for ethanol vapor concentration of 1000 ppm with the response time and recovery time were about 1 and 14 second, respectively.

475, 634.6 และ 772.5 cm^{-1} ในเส้นลวดนาโนสอดคล้องกับค่าที่อ่านได้จากผงดีบุกไดออกไซด์ จากการวัดสภาพนำไฟฟ้าของเส้นลวดนาโนเดี่ยวพบว่ามีความต้านทานประมาณ $4.8 (\Omega \cdot \text{cm})^{-1}$ จากนั้นนำเส้นลวดนาโนดีบุกไดออกไซด์มาใช้เป็นหัวตรวจวัดไอเอทานอล โดยที่การตอบสนองต่อเอทานอลของเส้นลวดนาโนดีบุกไดออกไซด์ สังเกตได้จากความต้านทานที่เปลี่ยนแปลงไปของหัวตรวจวัดเมื่อสัมผัสกับไอเอทานอลความเข้มข้นในช่วง 100-1000 ppm และอุณหภูมิของหัวตรวจวัดในช่วง $200-320^\circ\text{C}$ ซึ่งการตอบสนองต่อไอเอทานอลสูงสุดมีค่าประมาณ 54 เท่าเมื่ออุณหภูมิของหัวตรวจวัดเป็น 280°C ที่ความเข้มข้น 1000 ppm และเวลาในการตอบสนองและเวลาในการคืนตัวของหัวตรวจวัดมีค่าประมาณ 1 และ 14 วินาที ตามลำดับ